

THIN-WALL HEAT SHRINK TUBING 3:1 / 125°C



Technical description

Colour: Black

Materials: Crosslinked Polyolefin

Shrink ratio: 3:1

Flame retardant

Flammability: UL224 VW-1

Operating temperature: -55 °C +125 °C

Minimum shrink temperature: +70 °C

Minimum full recovery temperature: +100 °C

Longitudinal change 0 ± 10% massimo

All dimensions are in mm



Code	Before recovery: inside diameter	After recovery: inside diameter (max.)	After recovery: wall thickness (min.)	PKG.MT
14240RA01	1,6	0,5	0,45	150
14241RA01	3,2	1,1	0,50	150

Code	Before recovery: inside diameter	After recovery: inside diameter (max.)	After recovery: wall thickness (min.)	PKG.MT
14242RA01	4,8	1,6	0,6	75
14243RA01	6,4	2,1	0,65	75
14244RA01	9,5	3,2	0,75	75
14245RA01	12,7	4,2	0,80	50
14246RA01	19,1	6,4	0,90	30
14247RA01	25,4	8,5	1,0	30
14248RA01	39,0	13,0	1,20	30